



Schnittdatenempfehlung VHM 475W TS35

Parameters recommendation, Paramètres conseillés, Parametri di taglio indicativi



| Material | D [mm] | V _c [m/min] | f _z [mm] | a _p [mm] | a _e [mm] | n [min ⁻¹] | V _f [mm/min] | Q [cm ³ /min] |
|---|------------|------------------------|---------------------|---------------------|---------------------|------------------------|-------------------------|--------------------------|
| Baustahl Unlegierter Stahl <i>Structural steel</i> <i>Unalloyed steel</i> <i>Acier de construction</i> <i>Acier non allié</i> <i>Acciaio di costruzione</i> <i>Acciaio non legato</i> <800 N/mm ² | 4 | 160 (140-180) | 0,035 (0,01-0,06) | 7,0 | 1,80 | 12.730 | 1.780 | 23,1 |
| | 5 | 160 (140-180) | 0,035 (0,01-0,06) | 9,0 | 2,25 | 10.190 | 1.425 | 28,9 |
| | 6 | 160 (140-180) | 0,070 (0,05-0,09) | 11,0 | 2,70 | 8.490 | 2.375 | 69,3 |
| | 8 | 160 (140-180) | 0,090 (0,07-0,11) | 14,0 | 3,60 | 6.370 | 2.295 | 119,0 |
| | 10 | 160 (140-180) | 0,120 (0,10-0,14) | 18,0 | 4,50 | 5.090 | 2.445 | 198,0 |
| | 12 | 160 (140-180) | 0,140 (0,12-0,16) | 22,0 | 5,40 | 4.240 | 2.375 | 277,0 |
| | 16 | 160 (140-180) | 0,180 (0,16-0,20) | 29,0 | 7,20 | 3.180 | 2.290 | 474,9 |
| Werkzeugstahl Vergütungsstahl Legierter Stahl <i>Tool steel, heat-treatable steel,</i> <i>alloyed steel</i> <i>Acier à outil, acier par traitement</i> <i>thermique, acier allié</i> <i>Acciaio d'utensile, acciaio</i> <i>bonificato, acciaio legato</i> 800-1200 N/mm ² | 4 | 120 (90-150) | 0,035 (0,01-0,06) | 7,0 | 1,80 | 9.550 | 1.335 | 17,3 |
| | 5 | 120 (90-150) | 0,035 (0,01-0,06) | 9,0 | 2,25 | 7.640 | 1.070 | 21,7 |
| | 6 | 120 (90-150) | 0,070 (0,05-0,09) | 11,0 | 2,70 | 6.370 | 1.785 | 52,1 |
| | 8 | 120 (90-150) | 0,090 (0,07-0,11) | 14,0 | 3,60 | 4.770 | 1.715 | 88,9 |
| | 10 | 120 (90-150) | 0,120 (0,10-0,14) | 18,0 | 4,50 | 3.820 | 1.835 | 148,6 |
| | 12 | 120 (90-150) | 0,140 (0,12-0,16) | 22,0 | 5,40 | 3.180 | 1.780 | 207,6 |
| | 16 | 120 (90-150) | 0,180 (0,16-0,20) | 29,0 | 7,20 | 2.390 | 1.720 | 356,7 |
| Edelstahl Hochlegierter Stahl <i>High grade steel</i> <i>High alloyed steel</i> <i>Acier noble</i> <i>Acier fortement allié</i> <i>Acciaio superiore</i> <i>Acciaio di alta lega</i> | 4 | 100 (60-120) | 0,035 (0,01-0,06) | 7,0 | 1,80 | 7.960 | 1.115 | 14,5 |
| | 5 | 100 (60-120) | 0,035 (0,01-0,06) | 9,0 | 2,25 | 6.370 | 890 | 18,0 |
| | 6 | 100 (60-120) | 0,070 (0,05-0,09) | 11,0 | 2,70 | 5.310 | 1.485 | 43,3 |
| | 8 | 100 (60-120) | 0,090 (0,07-0,11) | 14,0 | 3,60 | 3.980 | 1.435 | 74,4 |
| | 10 | 100 (60-120) | 0,120 (0,10-0,14) | 18,0 | 4,50 | 3.180 | 1.525 | 123,5 |
| | 12 | 100 (60-120) | 0,140 (0,12-0,16) | 22,0 | 5,40 | 2.650 | 1.485 | 173,2 |
| | 16 | 100 (60-120) | 0,180 (0,16-0,20) | 29,0 | 7,20 | 1.990 | 1.435 | 297,6 |
| Titanlegierungen <i>Titanium alloys</i> <i>Alliage titane</i> <i>Leghe di titanio</i> >300 HB (z.B., e.g., p.ex., p.e. TiAlV6) | 4 | 60 (40-80) | 0,020 (0,01-0,06) | 7,0 | 1,00 | 4.770 | 380 | 2,7 |
| | 5 | 60 (40-80) | 0,020 (0,01-0,06) | 9,0 | 1,25 | 3.820 | 305 | 3,4 |
| | 6 | 60 (40-80) | 0,050 (0,03-0,09) | 11,0 | 1,50 | 3.180 | 635 | 10,3 |
| | 8 | 60 (40-80) | 0,070 (0,05-0,11) | 14,0 | 2,00 | 2.390 | 670 | 19,3 |
| | 10 | 60 (40-80) | 0,100 (0,08-0,14) | 18,0 | 2,50 | 1.910 | 765 | 34,4 |
| | 12 | 60 (40-80) | 0,120 (0,10-0,16) | 22,0 | 3,00 | 1.590 | 765 | 49,6 |
| | 16 | 60 (40-80) | 0,160 (0,14-0,20) | 29,0 | 4,00 | 1.190 | 760 | 87,6 |
| 20 | 60 (40-80) | 0,180 (0,16-0,24) | 36,0 | 5,00 | 950 | 685 | 123,3 | |



| Material | D [mm] | V _c [m/min] | f _z [mm] | a _p [mm] | a _e [mm] | n [min ⁻¹] | V _f [mm/min] | Q [cm ³ /min] |
|---|------------|------------------------|---------------------|---------------------|---------------------|------------------------|-------------------------|--------------------------|
| Baustahl Unlegierter Stahl <i>Structural steel</i> <i>Unalloyed steel</i> <i>Acier de construction</i> <i>Acier non allié</i> <i>Acciaio di costruzione</i> <i>Acciaio non legato</i> <800 N/mm ² | 4 | 160 (140-180) | 0,03 (0,01-0,05) | 4,0 | 4,0 | 12.730 | 1.530 | 24,5 |
| | 5 | 160 (140-180) | 0,03 (0,01-0,05) | 5,0 | 5,0 | 10.190 | 1.225 | 30,6 |
| | 6 | 160 (140-180) | 0,06 (0,04-0,08) | 6,0 | 6,0 | 8.490 | 2.040 | 73,4 |
| | 8 | 160 (140-180) | 0,08 (0,06-0,10) | 8,0 | 8,0 | 6.370 | 2.040 | 130,6 |
| | 10 | 160 (140-180) | 0,10 (0,08-0,12) | 10,0 | 10,0 | 5.090 | 2.035 | 203,5 |
| | 12 | 160 (140-180) | 0,12 (0,10-0,14) | 12,0 | 12,0 | 4.240 | 2.035 | 293,0 |
| | 16 | 160 (140-180) | 0,16 (0,14-0,18) | 16,0 | 16,0 | 3.180 | 2.035 | 521,0 |
| Werkzeugstahl Vergütungsstahl Legierter Stahl <i>Tool steel, heat-treatable steel,</i> <i>alloyed steel</i> <i>Acier à outil, acier par traitement</i> <i>thermique, acier allié</i> <i>Acciaio d'utensile, acciaio</i> <i>bonificato, acciaio legato</i> 800-1200 N/mm ² | 4 | 120 (90-150) | 0,03 (0,01-0,05) | 4,0 | 4,0 | 9.550 | 1.145 | 18,3 |
| | 5 | 120 (90-150) | 0,03 (0,01-0,05) | 5,0 | 5,0 | 7.640 | 915 | 22,9 |
| | 6 | 120 (90-150) | 0,06 (0,04-0,08) | 6,0 | 6,0 | 6.370 | 1.530 | 55,1 |
| | 8 | 120 (90-150) | 0,08 (0,06-0,10) | 8,0 | 8,0 | 4.770 | 1.525 | 97,6 |
| | 10 | 120 (90-150) | 0,10 (0,08-0,12) | 10,0 | 10,0 | 3.820 | 1.530 | 153,0 |
| | 12 | 120 (90-150) | 0,12 (0,10-0,14) | 12,0 | 12,0 | 3.180 | 1.525 | 219,6 |
| | 16 | 120 (90-150) | 0,16 (0,14-0,18) | 16,0 | 16,0 | 2.390 | 1.530 | 391,7 |
| Edelstahl Hochlegierter Stahl <i>High grade steel</i> <i>High alloyed steel</i> <i>Acier noble</i> <i>Acier fortement allié</i> <i>Acciaio superiore</i> <i>Acciaio di alta lega</i> | 4 | 100 (60-120) | 0,03 (0,01-0,05) | 4,0 | 4,0 | 7.960 | 955 | 15,3 |
| | 5 | 100 (60-120) | 0,03 (0,01-0,05) | 5,0 | 5,0 | 6.370 | 765 | 19,1 |
| | 6 | 100 (60-120) | 0,06 (0,04-0,08) | 6,0 | 6,0 | 5.310 | 1.275 | 45,9 |
| | 8 | 100 (60-120) | 0,08 (0,06-0,10) | 8,0 | 8,0 | 3.980 | 1.275 | 81,6 |
| | 10 | 100 (60-120) | 0,10 (0,08-0,12) | 10,0 | 10,0 | 3.180 | 1.270 | 127,0 |
| | 12 | 100 (60-120) | 0,12 (0,10-0,14) | 12,0 | 12,0 | 2.650 | 1.270 | 182,9 |
| | 16 | 100 (60-120) | 0,16 (0,14-0,18) | 16,0 | 16,0 | 1.990 | 1.275 | 326,4 |
| Titanlegierungen <i>Titanium alloys</i> <i>Alliage titane</i> <i>Leghe di titanio</i> >300 HB (z.B., e.g., p.ex., p.e. TiAlV6) | 4 | 60 (40-80) | 0,01 (0,01-0,05) | 4,0 | 4,0 | 4.770 | 190 | 3,0 |
| | 5 | 60 (40-80) | 0,01 (0,01-0,05) | 5,0 | 5,0 | 3.820 | 155 | 3,9 |
| | 6 | 60 (40-80) | 0,03 (0,02-0,08) | 6,0 | 6,0 | 3.180 | 320 | 11,5 |
| | 8 | 60 (40-80) | 0,04 (0,02-0,10) | 8,0 | 8,0 | 2.390 | 335 | 21,4 |
| | 10 | 60 (40-80) | 0,05 (0,03-0,10) | 10,0 | 10,0 | 1.910 | 380 | 38,0 |
| | 12 | 60 (40-80) | 0,06 (0,04-0,10) | 12,0 | 12,0 | 1.590 | 380 | 54,7 |
| | 16 | 60 (40-80) | 0,08 (0,06-0,12) | 16,0 | 16,0 | 1.190 | 380 | 97,3 |
| 20 | 60 (40-80) | 0,09 (0,06-0,14) | 20,0 | 20,0 | 950 | 340 | 136,0 | |